



Retail systems Fire ratings - Aug. 2010

The following are results of the ASTM E84 standard method for test for surface burning characteristics of building materials. Copies of complete test results are available upon request.

Note: Flame spread dictates class:

- I or A : 0-25
- II or B : 26-75
- III or C : 76-200

N/A indicates that product was not tested

This information supersedes all data previously published

** Note: the use of fire rated core will reduce the load capacity of the system. You will need to determine if it meets your needs.

Surface tested	Class		Flame Spread		Smoke Developed	
	<u>Slatwall</u>	<u>Slatwall</u>	<u>Slatwall</u>	<u>Slatwall</u>	<u>Slatwall</u>	<u>Slatwall</u>
	<u>Non-</u> <u>inserted</u>	<u>Aluminum</u> <u>insert</u>	<u>Non-</u> <u>inserted</u>	<u>Aluminum</u> <u>insert</u>	<u>Non-</u> <u>inserted</u>	<u>Aluminum</u> <u>insert</u>
Paint Grade	C	B	115	70	80	90
Painted	C	C	115	105	200	95
LPM	C	C	190	160	80	95
HPL	C	C	95	95	125	90
FR Core & Std HPL	N/A	A	N/A	20	N/A	35
FR Core & FR HPL	N/A	A	N/A	20	N/A	85



Dover, OH 44622 800-377-1221
www.marlite.com info@marlite.com