

	<h1>Technical Data</h1>	<b>Code:</b>	D-TC-040	
		<b>Revision:</b>	01	
	<b>Marlite FRP-EX</b> Wall Panel and Ceiling Tile - Class A – Pebbled and Smooth	<b>Effective since:</b>	6-Sep-2024	
		<b>Page:</b>	1 of 3	

### 1. Product description.

FM Approved Marlite Fiberglass Reinforced Plastic (FRP) Wall Panels and Ceiling Tile, manufactured by Marlite, are available in textured and smooth surfaces, provide ultimate durability, satisfying the most demanding applications. Marlite FRP-EX panels and ceiling tiles will not mold, mildew, rot or corrode. Marlite FRP-EX panels and ceiling tiles are engineered to provide durability, easy cleaning and maintenance.

### 2. Purpose.

Marlite FRP-EX panels and ceiling tiles are designed for indoors wall finishes that require a FM Approved fire rating product under the Approval Standard 4880. Marlite FRP-EX panels and ceiling tile applications range from restaurants and supermarkets to restrooms and storage areas.

### 3. Physical Properties - Typical Values

0.090in Nominal Thickness		
Property	Value	Test Method
Flexural Strength	18,000 psi	ASTM D790
Flexural Modulus	$1.69 \times 10^5$ psi	ASTM D790
Tensile Strength	5,000 psi	ASTM D638
Tensile Modulus	$6.86 \times 10^5$ psi	ASTM D638
% Elongation	1.08 %	ASTM D638
Izod Impact	4.38 ft-lb/in	ASTM D256
Coefficient of Linear Thermal Expansion	$2.91 \times 10^{-5}$ in/in/°F	ASTM E831
Barcol Hardness <sup>1</sup>	35	ASTM D2583
Abrasion Resistance	0.405 % Wt. Loss	Taber Test
Water Absorption	0.586 % - 72 hr @ 74°F	ASTM D570
Specific Gravity	1.807	ASTM D792
Flame Spread	≤ 25	ASTM E84
Smoke Density	≤ 450	ASTM E84

**Note:**

- ASTM standard has been discontinued without replacement by the ASTM Sponsoring Committee responsible for the Standard. ASTM makes withdraw standards available for informational purposes.

### 4. Selections

#### a. Wall Panel

Nominal Thickness	Finish	Color	Sizes
0.090 in	Pebbled	Bright White Almond Ivory Beige Light Gray Silver	4 ft x 8 ft 4 ft x 9 ft 4 ft x 10 ft 4 ft x 12 ft
	Smooth	Bright White	
0.075 in	Pebbled / Smooth	Bright White	4 ft x 8 ft 4 ft x 9 ft 4 ft x 10 ft 4 ft x 12 ft

	<b>Technical Data</b>		<b>Code:</b>	D-TC-040
			<b>Revision:</b>	01
	<b>Marlite FRP-EX</b>		<b>Effective since:</b>	6-Sep-2024
	Wall Panel and Ceiling Tile - Class A – Pebbled and Smooth		<b>Page:</b>	2 of 3

### b. Ceiling Tile

Nominal Thickness	Finish	Color	Sizes
0.090 in	Pebbled / Smooth	Bright White	2 ft x 4 ft 4 ft x 4 ft

## 5. Standard Specifications

- a) Marlite FRP-EX panels conform to the specification set on ASTM D5319:
  - Flammability Classification: Class A - Flame spread index 0 to 25, smoke development index of 450 or less.
  - Thickness classifications:
    - Grade 5—0.067 to 0.083 in. (1.70 to 2.11 mm); 0.075 in. nominal (1.91 mm).
    - Grade 6—0.081 to 0.099 in. (2.06 to 2.51 mm); 0.090 in. nominal (2.29 mm).
  - Size (Length and Width): Specified length and width  $\pm 1/8$  in.
  - Squareness:  $\pm 1/8$  in.
  - Thickness: Specified thickness  $\pm 10$  %.
- b) Color: Panel color shall be per specification. Within 1 dE of the specified color using the CIELab scale.
- c) Panels shall have a pebbled texture or smooth texture front side. Panel backside is smooth and may possess slight imperfections that do not adversely affect performance or physical properties and are not cause for rejection.
- d) Panels shall be installed in strict accordance with Marlite Standard FRP- panel Installation Instructions.

## 6. Approvals and Certifications

- a) Manufactured on an ISO 9001 Certified plant.
- b) Approved Product under FM Approval Standard 4880 - Class 1 Fire Rating of Building Panels or Interior Finish Materials
- c) Meets minimum requirements of major model building codes for Class A interior wall and ceiling finishes of flame spread  $\leq 25$ , smoke developed index 450 or less (per ASTM E84).


## 7. Storage Recommendations

- a) Store panels indoors in a cool, dry, well-ventilated area.
- b) Panels should be stacked on skids not more than 5 skids high.
- c) Do not allow moisture to collect on or in-between panels.

## 8. Installation Overview

- a) Safety: Use eye protection. Wear filter mask to cover nose and mouth, especially when cutting panels.
- b) Tools Required: Power saw (carbide tip), saber saw (metal cutting blade), caulking gun, tape measurer, drill, file, hammer, level, sawhorses and supports.
- c) Preparation: It is important to store Marlite FRP-EX flat on a clean, dry surface for 24 hours before installation. It is preferable to store them inside the actual area of installation or, at least, under similar climate conditions. Walls must be clean and free of all substances. Level any high or low spots on walls. Concrete block walls may require a leveling coat of plaster or other similar material.
- d) Inspection: Carefully inspect all panels prior to installation. If any portion of material does not provide an acceptable appearance, Marlite should be notified immediately. Upon verification of unacceptability, that portion of material will be replaced by Marlite. Marlite's responsibility is for the replacement of defective materials but not for labor or other handling or installation expenses.
- e) Limitations: Marlite FRP-EX panels shall maintain its performance characteristics and physical properties in temperatures ranging from -40°F to 130°F. Marlite FRP-EX panels may discolor near heat sources such as: ovens, fryers, heat lamps and toasters, where temperatures exceed 130°F.

	<h1>Technical Data</h1>	<b>Code:</b>	D-TC-040
		<b>Revision:</b>	01
	<b>Marlite FRP-EX</b> Wall Panel and Ceiling Tile - Class A – Pebbled and Smooth	<b>Effective since:</b>	6-Sep-2024
		<b>Page:</b>	3 of 3



**DISCLAIMER:** Marlite provides these results data for material comparison purposes only. The information offered herein is offered without charge and is accepted at recipient's sole risk. The results expressed of this document pertain only to the specific sample(s) evaluated. Marlite's Testing Laboratory is not a certified testing lab, however all equipment used is calibrated using traceable standards. Because conditions of use vary and are beyond our knowledge and control, Marlite makes no representation about and is not responsible for the accuracy of data, nor with toxicological effect or industrial hygiene requirements associated with particular uses of any product or process described herein. Marlite requests that customers test and inspect our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, nor is protection from any law or patent inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of Marlite materials only. **FLAME SPREAD AND SMOKE DEVELOPMENT RATINGS:** the numerical flame spread and smoke development ratings are not intended to reflect alleged hazards presented by Marlite, products under actual fire conditions and this product has not been tested by Marlite, except as set forth below. These ratings are determined by small-scale tests conducted by independent testing facilities using the ASTM E84 test standard. Like other organic building materials (e.g. wood), panels made of fiberglass reinforced plastic resins will burn. When ignited, FRP may produce dense smoke very rapidly. All smoke is toxic. Fire safety requires proper design of facilities and fire suppression systems, as well as precautions during construction and occupancy. Local codes, insurance requirements and any special needs of the product user will determine the correct fire-rated interior finish and fire suppression system necessary for a specific installation.